



RESINA A LETTO MISTO

Resine a letto misto rigenerabili pronte all'uso. Idonee per la produzione di acqua ultra pura con valori inferiori a 0,1 us/cm..

Resine equivalenti:

- Dowex MB50;
- Purolite MB46, MB47;
- Rhom and Haas: MB20;
- Bayer: Levatit SM94.

OH⁻ Form

H⁺ Form

	OH ⁻ Form	H ⁺ Form
Polymer Matrix Structure	Gel PolyStyrene Crosslinked with DVB	
Functional Group	Quaternary Amine	Sulfonic acid
Volume ratio	1.1 parts	0.9 part
Total Exchange Capacity, min. eq/l	1,25	1,80
Water Retention Capacity %	53-58	45-50
Particle Size Distribution		
>1.25 mm max. %	5	5
<0.40 mm, max %	2	2
Whole Bead Count, min. %	95	95
Moisture Content as shipped, max	65%	
PH Range, Stability	0-14	
Shipping weight (approx.)	700-780 g/l	
Ionic conversion, min. %	90	99

